

## PREFACE

---

The scientific community is focusing on energy storage options due to the current energy crisis and severe air pollution resulting from burning of conventional fossil fuels. There is a significant demand for the research and development of innovative, environmentally friendly energy systems and associated energy storage technologies. Dielectric capacitors show promise as energy storage systems in various applications such as transportation and portable electronic devices, thanks to their high-power density, long lifespan, and extensive cyclic life. However, their energy density is comparatively low as compared to conventional batteries, hindering efforts to further improve these storage devices<sup>1</sup>. Despite this limitation, capacitors have a crucial role in energy storage technologies due to their rapid charging and discharging capabilities, which batteries lack.

Dielectric capacitors typically consist of dielectric materials with excellent storage properties. Ceramic dielectrics exhibit a high dielectric constant, low dielectric loss, and a broader temperature operating range. However, due to the toxic nature of common lead based dielectrics, their use is limited in research. BaTiO<sub>3</sub>-based electro-ceramics present a potential alternative to lead-based dielectrics, offering breakdown strength of 145-450 kV/cm.<sup>2</sup> Over the past few years, many other electro ceramics with comparable dielectric strength and energy density have been developed. However, their lower dielectric breakdown strength limits their application in power electronics.

On other hand, polymers are characterized by lower dielectric constants, high energy storage density, and high dielectric breakdown strength. When compared to dielectric ceramics, the dielectric constant of dielectric polymers is notably lower. Noteworthy examples include Polyvinylidene fluoride (PVDF), Biaxially Oriented Polypropylene (BOPP), and Poly(methyl methacrylate) (PMMA) with reported dielectric

constant values of  $\sim 10$ ,  $\sim 2$ , and  $5$  respectively<sup>2</sup>. To tailor these polymers for energy storage applications, researchers often modify them by synthesizing nanocomposites, using the polymer as a matrix. PVDF, in particular, has drawn significant attention due to its exceptional dielectric properties, prompting extensive research to enhance these properties further. Basically, PVDF based polymer nanocomposites have been synthesized using conducting/semiconducting and nonconducting fillers.

Nanoparticles with semiconducting/conducting properties have been investigated as nanofillers within the PVDF matrix to enhance its dielectric properties. PVDF based composites with conducting/semiconducting filler can exhibit high dielectric permittivity with proper proportion of filler loading. High dielectric permittivity can only be achieved when the filler loading is very close to and less than the percolation threshold. Many synthesized PVDF-based polymer nanocomposites have shown promising outcomes. Such high permittivity values have been reported in various percolative polymer composites with different conductive/semiconducting particles, including metal particles, carbon nanofibers, CNTs, graphene, TiO<sub>2</sub> and ZnO<sup>3-6</sup>. Optimal energy density has been achieved up to a specific vol% of such nanofillers, but excessive filler amounts can cause percolation in nanocomposites, compromising their properties. The nanocomposites transition into behaving partially conducting beyond the percolation threshold, creating numerous conducting paths in composite films. Although polymer nanocomposite with conductive filler have successfully achieved favourable dielectric permittivity and low percolation threshold, they still face ongoing challenges including elevated dielectric loss, diminished dielectric strength, and a limited processing window that significantly hinder their applications in high energy storage application. The incorporation of conductive fillers increases dielectric permittivity in nanocomposites because of Maxwell Wagner Sillars (MWS) polarization or micro capacitor effect, yet it concurrently leads to high dielectric

loss and leakage current via conductive particle network formed near critical percolation threshold, which causes a drastic reduction in breakdown strength<sup>7,8</sup>. One frequently cited explanation for this phenomenon is that the development of micro capacitors results in an unusually expansive local electric field within the pristine polymer region due to the close proximity of adjacent nanoparticles. As the polymer layer between these neighboring particles is excessively thin to withstand the escalating local electric field, it leads to a short circuit, giving rise to a substantial leakage current<sup>7</sup>.

On the other hand, PVDF based nanocomposites using nonconducting/ceramic filler have also been synthesized for energy storage applications. High dielectric constant ceramics, such as BaTiO<sub>3</sub>, lead-based and SrTiO<sub>3</sub>, have been employed as fillers to reinforce in the PVDF matrix<sup>9</sup>. The incorporation of these fillers has resulted in increased dielectric constant and polarization, consequently boosting the energy storage density of the polymer nanocomposites. There appears to be less limitation in the reinforcement of dielectric ceramics in PVDF, with fillers reaching over 50 vol% to achieve the desired energy density and dielectric properties in comparison to PVDF based nanocomposites using conducting filler. For instance, reinforcing 60 vol% BaTiO<sub>3</sub> in the PVDF matrix elevated the dielectric constant from ~9 to ~125, with surface modification of the filler using Polyvinylpyrrolidone (PVP)<sup>2</sup>. Recent research indicates that the energy density of PVDF/BaTiO<sub>3</sub> nanocomposites is optimal at 3 vol% filler loading. Other surfactants like H<sub>2</sub>O<sub>2</sub>, ethylene diamine, -NH<sub>2</sub>, polydopamine (PDOPA) have been successfully used to modify the surface of the nanofillers to get improved dielectric and energy storage properties in various reported literature<sup>1,10</sup>.

In our current research, we have chosen PVDF as polymer for developing nanocomposites with different nonconducting/ceramic BaTiO<sub>3</sub> based ceramics for high-energy storage applications. PVDF can exist in four crystalline phases namely  $\alpha$  as a

nonpolar phase,  $\beta$ ,  $\gamma$  and  $\delta$  as polar phases. By employing suitable processing methods or forming nanocomposites with appropriate ceramics and polymer, the nonpolar phase of PVDF can be converted into electroactive polar phases. Ceramic fillers have been used to enhance the dielectric and energy storage properties of the nanocomposites. Our investigation into these nanocomposites has yielded several noteworthy findings, briefly outlined below.

### **1. Energy storage properties of cold sintered $\text{Ba}_{0.7}\text{Sr}_{0.3}\text{TiO}_3$ /PVDF Polymer Ceramic Nanocomposites**

$\text{Ba}_{0.7}\text{Sr}_{0.3}\text{TiO}_3$ /PVDF (Polyvinylidene fluoride) ceramic-polymer composites have been synthesized using a cold sintering process.  $\text{Ba}_{0.7}\text{Sr}_{0.3}\text{TiO}_3$  (BST) nanoparticles are synthesized using sol-gel combustion method. The BST nanoparticles are used for synthesizing the  $\text{Ba}_{0.7}\text{Sr}_{0.3}\text{TiO}_3$ -PVDF composite with 80wt.% BST and 20 wt. % PVDF. X-ray diffraction analysis confirmed pure phase formation of BST and revealed presence of different phases of PVDF in certain conditions. XRD pattern confirms the formation of pure perovskite phase of BST with cubic structure having Pm-3m space group. In case of BST/PVDF composite, crystallization of  $\beta$  phase and in case of annealed BST/PVDF composite, crystallization of  $\gamma$ -phase dominates. Thermal stability and surface morphology of the composite has been studied using thermo-gravimetric analysis and SEM respectively. TGA/DSC analysis reveals that composite is stable for the application up to 300 °C. Dielectric and ferroelectric properties have been studied. Thermally stable dielectric constant and dielectric loss is obtained from room temperature to 200 °C in case of annealed BST/PVDF composites. Polarization-Electric field hysteresis loop analysis of composite reveals that significantly higher dielectric breakdown strength (more than 400 kV/cm) have been achieved in comparison to pure ceramic which is the main criteria for a potential material for energy storage purpose. Discharge efficiency of BST/PVDF annealed

composite upto 95 % and high thermal stability up to 300 °C has been achieved in case of BST/PVDF annealed composite which is big achievement for a ceramic matrix composite with polymer filler.

## **2. BaZrO<sub>3</sub>/Poly (Vinylidene difluoride) Ceramic Nanocomposite Films with Improved Dielectric and Energy Storage Properties**

BaZrO<sub>3</sub> (BZ)/PVDF (Polyvinylidene difluoride) Polymer nanocomposites have been synthesized for energy storage applications using solution casting method. Barium zirconate (BZ) has been synthesized using high energy ball mill method and BZ/PVDF ceramic nanocomposites have been synthesized in thin film form using 90 wt. % PVDF polymers as a matrix and 10 wt.% BZ as nanofillers. XRD analysis has been performed to check successful synthesis of nanocomposites. We have synthesized pure PVDF film, BZ/PVDF and hydroxylated (hy)-BZ/PVDF composite film and we have achieved value of dielectric constant for the hy-BZ/PVDF composite film ( $\epsilon_r \sim 26$ ) almost three times of the value of dielectric constant for pure PVDF film. FTIR spectra of hy-BZ powder shows the successful hydroxylation of BaZrO<sub>3</sub> filler. TGA curve shows that there is no weight loss observed upto 450<sup>0</sup>C in case of composites. XPS and AFM analysis has also been performed for above synthesized composites. Polarization has been also increased upto almost double in case of hy-BZ/PVDF composite in comparison to pure PVDF film. We have achieved energy storage density of 1.11 J/cm<sup>3</sup> for hy-BZ/PVDF composite much higher than the pure PVDF which is equal to 0.47 J/cm<sup>3</sup>. The dielectric breakdown strength has also been analysed using Weibull analysis technique and obtained 1495 kV/cm in case of hy-BZ/PVDF composites.

### **3. BaZr<sub>0.4</sub>Ti<sub>0.6</sub>O<sub>3</sub>/Poly (Vinylidene fluoride) Composite Films with Improved Dielectric and Energy Storage Properties**

We have synthesized BaZr<sub>0.4</sub>Ti<sub>0.6</sub>O<sub>3</sub> (BZT) ceramic nanoparticles using nano mill process and hydroxylated (hy)-BZT/PVDF composite film using solution casting method with 10 wt. % of BZT nanoparticle as filler and 90 wt. % of PVDF polymer as a matrix. XRD patterns of composites confirm the successful formation of composites. FTIR spectra confirms the successful hydroxylation of BZT powder for better dispersion. Differential scanning calorimetry analysis represents improved degree of crystallinity in case of composites. AFM analysis has also been performed for synthesized composites. The dominance of polar phase of PVDF in composites was observed due to interfacial interaction among filler nanoparticles. The significantly enhanced dielectric permittivity ( $\epsilon_r \sim 25.5$ ) and ferroelectric properties have been obtained in case of hy-BZT/PVDF composite film in comparison to pure PVDF film ( $\epsilon_r \sim 8$ ). The value of dielectric breakdown strength for hy-BZT/PVDF composite has been calculated using Weibull analysis and found to be 1754 kV/cm. We have calculated energy storage density using Weibull analysis for hy-BZT/PVDF composite and was found to be 0.41 J/cm<sup>3</sup> at electric field of 790 kV/cm. The above synthesized composites may be a suitable replacement with improved dielectric properties for energy storage applications.

The thesis is organized into six chapters.

**Chapter-I:** This chapter describes basic introduction about energy storage materials. The basic concepts related to dielectric materials, energy storage in various dielectric materials, energy density and dielectric breakdown strength have been discussed in detail. The brief review of the reported literature on polymer based composite materials using conducting/semiconducting and nonconducting filler for energy storage applications has been discussed. Objective of the present thesis work is discussed in the last of the chapter.

**Chapter-II:** This chapter describes different synthesis methods for ceramic and PVDF based polymer ceramic nanocomposite materials. Cold sintering process and solution casting method for PVDF based polymer ceramic composites have been described in detail. The use of different materials and chemicals has also been discussed. The various characterization techniques used in the study of various synthesized composites have also been discussed in this chapter.

**Chapter-III:** This chapter involves synthesis of PVDF polymer-based nanocomposites using BST ceramic as a matrix and PVDF polymer as a filler with the help of cold sintering technique. Experimental results obtained from synthesized samples have been discussed using various characterization techniques. The dielectric properties, energy storage properties and dielectric breakdown strength have been discussed in detail. Experimental results obtained in this chapter has been published in the **Journal of Materials Science: Materials in Electronics 34 (2023) 1939**.

**Chapter-IV:** In this chapter, we have described synthesis of hy-BaZrO<sub>3</sub>/PVDF nanocomposite films with the help of solution casting process using 90 wt. % PVDF polymer as a matrix and 10 wt.% BZ as nanofiller. We have achieved higher dielectric constant for the hy-BZ/PVDF composite film ( $\epsilon_r \sim 26$ ) almost three times in comparison to pure PVDF film and energy storage density 1.11 J/cm<sup>3</sup> for hy-BZ/PVDF composite much higher than the pure PVDF which is equal to 0.47 J/cm<sup>3</sup>. The dielectric breakdown strength has also been analysed using Weibull analysis technique and found to be 1495 kV/cm in case of hy-BZ/PVDF composites.

**Chapter-V:** Synthesis of PVDF based nanocomposites with reinforced BZT as a filler has been performed and energy storage properties have been studied. Significant improvement in the value of dielectric constant has been obtained in case of hy-BZT/PVDF

nanocomposites in comparison to pure PVDF film. The value of dielectric breakdown strength for hy-BZT/PVDF composite has been calculated using Weibull analysis and found to be 1754 kV/cm.

**Chapter-VI:** This chapter summarizes the outcome of present thesis work and future scope in this area.